

- GI*  
*amended*
- a) dispersing a calcined product of stimuable phosphor in a dispersion medium, to obtain a slurry;
  - b) eliminating grains that are of at least a predetermined size from the slurry of step a), using wet classification;
  - c) adding to the slurry of step b), a binder that is substantially soluble therein, to prepare a coating material; and
  - d) applying the coating material to a support and drying to thereby form a phosphor layer.
- 

14. (Amended) A method for manufacturing a radiation image conversion panel, comprising the steps of:

- 12*
- a) dispersing a calcined product of stimuable phosphor in a dispersion medium, to obtain a slurry;
  - b) eliminating grains that are of at least a predetermined size from the slurry of step a), using wet classification;
  - c) substituting the dispersion medium with a solvent capable of substantially dissolving the binder, while maintaining a slurry in steps (a) - (c);
  - d) adding to the slurry of step c), a binder that is substantially soluble therein, to prepare a coating material; and

d) applying the coating material to a support and drying to  
thereby form a phosphor layer.

---

C2  
could